

## PROFICIENCY TESTING PLAN

**ZO 2025/1 – Steel Testing  
(ZO 6892)**

**Proficiency Testing Provider at the SZK FAST  
Veveří 95, 602 00 Brno  
Czech Republic**

**szk.fce.vutbr.cz  
ptprovider.cz**

Coordinator  
Supervisor  
Approved for PT Provider

Assoc. Prof. Ing. Tomáš Vymazal, Ph.D.  
Ing. Petr Misák, Ph.D.  
Assoc. Prof. Ing. Tomáš Vymazal, Ph.D.

Approved: January 28, 2025  
Approved: January 28, 2025  
Approved: January 28, 2025

## Contents

<b>1 Basic Information about the Proficiency Testing Program</b>	<b>2</b>
<b>2 Implementation of the Proficiency Testing Program</b>	<b>2</b>
2.1 Testing on B500B concrete reinforcing bars . . . . .	2
2.2 Testing on the test rod . . . . .	3
2.3 Ensuring Homogeneity and Stability . . . . .	4
2.4 Instructions for Eliminating Major Sources of Errors and Risks . . . . .	4
2.5 PTP Schedule . . . . .	4
<b>3 Procedures used in the Statistical Analysis of Laboratory Results</b>	<b>4</b>
<b>4 Certificate of Participation and the Final Report on the Results of Interlaboratory Comparison</b>	<b>5</b>
<b>5 Safeguards for Confidentiality</b>	<b>5</b>
<b>6 Related Documents</b>	<b>5</b>

## 1 Basic Information about the Proficiency Testing Program

The aim of the Proficiency Testing Program (PTP) is to compare and evaluate the results of tests conducted on steel according to EN ISO 6892-1 [1].

The program strives to provide objective information about the measuring skills of PTP participants. The basic criterion for participation is timely registration for the program, and the prerequisites for obtaining the Certificate of Participation and the Final Report on the Results of Interlaboratory Comparison are timely payment of the fee and adherence to the schedule.

### Important dates:

<b>Registration deadline:</b>	<b>August 31, 2025</b>
<b>Distribution of samples:</b>	<b>October 13–17, 2025</b>
<b>Realization/initiation of testing:</b>	<b>October 11, 2025</b>
<b>Results sent to the organizer:</b>	<b>November 28, 2025</b>
<b>Evaluation/presentation of Certificate of Participation:</b>	<b>January 31, 2026</b>

**Submit of test results** – exclusively via <http://ptprovider.cz/OutcomesCode>. To log in, it is necessary to enter the participant's code, which is automatically sent when registering in PTP.

## 2 Implementation of the Proficiency Testing Program

Testing laboratories and other institutions interested can register for the PTP. The minimum number of participants is 5. If the number of participants is close to the minimum, the coordinator will consider the evaluation of PTP results using Horn's procedure to determine the assigned value and measurement uncertainty. The maximum number of participants is 30. If the minimum number of participants is not reached, the PT Provider reserves the right to cancel the PTP. This takes place according to Chapter 3 of the "Cancellation and Complaint Proceedings" instructions [2] available on <http://ptprovider.cz/?lang=en>.

### 2.1 Testing on B500B concrete reinforcing bars

#### 1. EN ISO 6892-1 [1]

- Characteristics: Tensile strength
- Units: N/mm<sup>2</sup>
- Specification according to EN 10027-1 [3]: B500B
- Testing specimens: Bars  $\phi$  10 mm, length 500 mm
- Number of determinations: 6
- For the evaluation, use the nominal cross-sectional area.

#### 2. EN ISO 6892-1 [1]

- Characteristics: Yield strength
- Units: N/mm<sup>2</sup>
- Specification according to EN 10027-1 [3]: B500B
- Testing specimens: Bars  $\phi$  10 mm, length 500 mm
- Number of determinations: 6
- For the evaluation, use the nominal cross-sectional area.

#### 3. EN ISO 6892-1 [1]

- Characteristics: Percentage elongation after fracture
- Units: %

- Specification according to EN 10027-1 [3]: B500B
- Testing specimens: Bars  $\phi$  10 mm, length 500 mm
- Number of determinations: 6

#### 4. EN ISO 6892-1 [1]

- Characteristics: Percentage reduction of area
- Units: %
- Specification according to EN 10027-1 [3]: B500B
- Testing specimens: Bars  $\phi$  10 mm, length 500 mm
- Number of determinations: 5

## 2.2 Testing on the test rod




Figure 1: Test specimen (rod)

#### 5. EN ISO 6892-1 [1]

- Characteristics: Tensile strength
- Units: N/mm<sup>2</sup>
- Specification according to EN ISO 898-1 [4]: strength class 4.8
- Testing specimens: see Figure 1
- Number of determinations: 6
- For the evaluation, use the nominal cross-sectional area.

#### 6. EN ISO 6892-1 [1]

- Characteristics: Yield strength
- Units: N/mm<sup>2</sup>
- Specification according to EN ISO 898-1 [4]: strength class 4.8
- Testing specimens: see Figure 1
- Number of determinations: 6
- For the evaluation, use the nominal cross-sectional area.

#### 7. EN ISO 6892-1 [1]

- Characteristics: Percentage elongation after fracture
- Units: %
- Specification according to EN ISO 898-1 [4]: strength class 4.8

- Testing specimens: see Figure 1
- Number of determinations: 6

#### 8. EN ISO 6892-1 [1]

- Characteristics: Percentage reduction of area
- Units: %
- Specification according to EN ISO 898-1 [4]: strength class 4.8
- Testing specimens: see Figure 1
- Number of determinations: 5

## 2.3 Ensuring Homogeneity and Stability

PT Provider employees and any suppliers they may utilize are aware of the significance of the homogeneity and stability of test specimens for the results of the Proficiency Testing Program. The homogeneity and stability of specimens is ensured in the following ways:

1. samples are from one production charge,
2. the distribution of specimens made of more production charge so as to ensure homogeneity of bodies in the field of testing of related characteristics,
3. by review the material before releasing participants.

## 2.4 Instructions for Eliminating Major Sources of Errors and Risks

PTP participants have the obligation:

- to handle the proficiency testing materials in the same way they handle the majority of routinely tested samples,
- to follow the instructions of the PT Provider employee responsible for the PTP, especially regarding the type of testing carried out, the number of result determinations and the PT schedule,
- to state measurement uncertainties in accordance with their documented procedures, including the corresponding expansion coefficient. Participants will use expansion coefficient 2, which approximately represents the 95 % reliability level, unless stated otherwise,
- adhere to the rules and principles of ethical behavior, avoiding unfair practices that could negatively impact the evaluation of the PT program,
- follow occupational health and safety and fire protection regulations, using only electrical equipment and instruments with valid inspections,
- to send the test results obtained during proficiency testing, including measurement uncertainties, to the PT Provider by the set deadline (see part 1).

## 2.5 PTP Schedule

All other information, forms and records not included in this document are accessible in updated form at <http://ptprovider.cz/?lang=en>.

## 3 Procedures used in the Statistical Analysis of Laboratory Results

Procedures used in the statistical analysis of proficiency testing programs can be found here: <http://ptprovider.cz/?lang=en>.

## 4 Certificate of Participation and the Final Report on the Results of Interlaboratory Comparison

The PT Provider gives expert commentary on participant efficiency evaluation in the Final Report as part of training courses the PT Provider organises. The Final Report preserves the anonymity of the PTP participants. Each participant, or the participant's test results, is represented by an ID number. The Certificate of Participation in the PT programme is part of the Final Report. The Certificate is unique to each participant and includes the participant's ID number.

## 5 Safeguards for Confidentiality

The identity of PTP participants is confidential and only known to persons/subjects involved with the PTP. All participant information is considered confidential by the PT Provider. The participant may renounce this confidentiality for the purposes of discussion and mutual assistance until the PTP results are obtained. The PT Provider reveals the proficiency testing results to no third party with the sole exception of a written request by a regulatory authority submitted prior to the commencement of the PTP and which has been granted a written consent by the PTP participants.

## 6 Related Documents

- Quality Handbook of the PT Provider at the SZK FAST
- Cancellation and Complaint Proceedings available at <http://ptprovider.cz/?lang=en> [2]
- MPA 20 – 01 - . . . for application of EN ISO/IEC 17043 Concordance Assessment – General Requirements for Proficiency Testing in the Accreditation System of the Czech Republic.

## References

- [1] EN ISO 6892-1. *Metallic materials - Tensile testing - Part 1: Method of test at room temperature*. 2021.
- [2] *Cancellation and Complaint Proceedings* – available at [www.ptprovider.cz](http://www.ptprovider.cz).
- [3] EN 10027-1. *Designation systems for steels - Part 1: Steel names*. 2017.
- [4] EN ISO 898-1. *Mechanical properties of fasteners made of carbon steel and alloy steel - Part 1: Bolts, screws and studs with specified property classes - Coarse thread and fine pitch thread*. 2013.