



PROFICIENCY TESTING PLAN

ZZB 2027/1 – Strength and durability of hardened concrete

Poskytovatel zkoušení způsobilosti při SZK FAST

Veveří 95, 602 00 Brno

Czech Republic

www.szk.fce.vutbr.cz

www.ptprovider.cz

Coordinator

Supervisor

Approved for PT
Provider

Assoc. Prof. Ing. Tomáš Vymazal, Ph.D.

Ing. Petr Misák, Ph.D.

Assoc. Prof. Ing. Tomáš Vymazal, Ph.D.

Approved: August 21, 2026

Approved: August 21, 2026

Approved: August 21, 2026

Contents

1 Basic Information about the Proficiency Testing Program	2
2 Implementation of the Proficiency Testing Program	2
2.1 Specifications and Characteristics	2
2.2 Ensuring Homogeneity and Stability	5
2.3 Instructions for Eliminating Major Sources of Errors and Risks	5
3 Procedures used in the Statistical Analysis of Laboratory Results	6
4 Certificate of Participation and the Final Report on the Results of Interlaboratory Comparison	6
5 Safeguards for Confidentiality	6
6 Related Documents	6

1 Basic Information about the Proficiency Testing Program

The aim of the Proficiency Testing Program (PTP) is to compare and evaluate the results of tests conducted on hardened concrete in compliance with selected parts of ČSN EN 12390-3 [1], ČSN EN 12390-7 [2], ČSN EN 12390-8 [3], ČSN EN 480-11 [4], ČSN 731322 [5], ČSN 731324 [6], ČSN 731326, metoda A [7], ČSN 731326, metoda C [7] and ČSN EN 12390-9 [8].

The program strives to provide objective information about the measuring skills of PTP participants. The basic criterion for participation is timely registration for the program, and the prerequisites for obtaining the Certificate of Participation and the Final Report on the Results of Interlaboratory Comparison are timely payment of the fee and adherence to the schedule.

Important dates:

Registration deadline:	January 30, 2027
Distribution of samples:	April 19, 2027
Realization/initiation of testing:	May 10, 2027
Results sent to the organizer:	July 14, 2027
Presentation of the Certificate of Participation:	August 31, 2027

Submission of test results takes place exclusively via the MyPT customer zone at <https://test.ptprovider.cz/zona>. Results are entered by the laboratory after signing in to their account, in the section of the respective programme.

2 Implementation of the Proficiency Testing Program

2.1 Specifications and Characteristics

Testing laboratories and other institutions interested can register for the PTP. The minimum number of participants is 5. If the number of participants is close to the minimum, the coordinator will consider the evaluation of PTP results using Horn's procedure to determine the assigned value and measurement uncertainty. If the minimum number of participants is not reached, the PT Provider reserves the right to cancel the PTP. This takes place according to Chapter 3 of the "Cancellation and Complaint Proceedings" instructions [9] available on ptprovider.cz. The maximum number of participants is 40.

Parts of the PT program:

ZZB01 ČSN EN 12390-3 [1]

- Characteristics: Compressive strength
- Unit: N/mm²
- Specification according to EN 206 [10]: C 30/37
- Testing specimens: 150 x 150 x 150 mm
- Number of observations: 3

- Use the water storage before testing.

ZZB02 ČSN EN 12390-7 [2]

- Characteristics: Weight Density
- Unit: kg/m³
- Specification according to EN 206 [10]: Ordinary concrete
- Testing specimens: 150 x 150 x 150 mm
- Number of observations: 3
- Instructions:
 1. Perform with the specimens prior to compressive strength testing according to EN 12390-3 [1].
 2. Use the water storage before testing.

ZZB03 ČSN EN 12390-8 [3]

- Characteristics: Depth of penetration of water under pressure
- Unit: mm
- Specification according to EN 206 [10]: XF2
- Testing specimens: 150 x 150 x 150 mm
- Number of observations: 3
- Instructions:
 1. Perform with any side face of the cubes, i.e. not the top nor bottom.
 2. The sides of the cubes have been treated according to article 7.1 of EN 12390-8 [3].

ZZB04 ČSN EN 480-11 [4]

- Characteristics: Total air content; A300; L
- Unit: %, %, mm
- Specification according to EN 206 [10]: 3 – 7
- Testing specimens: 150 x 150 x 150 mm
- Number of observations: 1 (2 specimens)
- Instructions:
 1. The samples will be prepared by the participants themselves according to article 6 in EN 480-11[4].
 2. The mixture formula will be provided by the organiser.

ZZB05 ČSN 731322 [5]

- Characteristics: Freeze-thaw resistance
- Unit: -
- Specification according to EN 206 [10]: C30/37
- Testing specimens: 100 x 100 x 400 mm

- Number of observations: 3+3 (100 cycles)
- Instructions:
 1. For the determination of the observed property of hardened concrete, 6 beam specimens sized 100 x 100 x 400 mm will be provided.
 2. Record the results after 100 cycles.
 3. Freezing and thawing takes place in cycles for concretes exposed to temperatures as low as -20°C.
 4. Frost resistance coefficient is the ratio of the arithmetic average of flexural strength of the frozen beams to the arithmetic average of flexural strength of reference beams.

ZZB06 ČSN 731324 [6]

- Characteristics: R_o
- Unit: %
- Specification according to EN 206 [10]: -
- Testing specimens: 7.07 x 7.07 x 7.07 mm
- Number of observations: 3/6
- Instructions: 3 or 6 cube specimens sized 7.07mm ± 2% (depending on the number of participants) will be supplied for the determination of the observed property of hardened concrete.

ZZB07 ČSN 731326, metoda A [7]

- Characteristics: Freeze-thaw resistance
- Unit: g/m²
- Specification according to EN 206 [10]: XF2
- Testing specimens: 150 x 150 x 150 mm
- Number of observations: 3 x 100 cycles
- Instructions: Three cube specimens sized 150 mm will be provided by the organiser for the determination of the observed property of hardened concrete.

ZZB08 ČSN 731326, metoda C [7]

- Characteristics: Freeze-thaw resistance
- Unit: g/m²
- Specification according to EN 206 [10]: XF2
- Testing specimens: Cylinder 50 x 150mm
- Number of observations: 3 x 75 cycles
- Instructions: 3 cylinder specimens (offcuts) of 150 mm in diameter and 50 mm height will be supplied for the determination of the observed property of hardened concrete.

ZZB09 ČSN EN 12390-9 [8]

- Characteristics: Freeze-thaw resistance – Scaling

- Unit: g/m²
- Specification according to EN 206 [10]: XF2
- Testing specimens: 2 cubes - 150 x 150 x 150 mm
- Number of observations: 4

2.2 Ensuring Homogeneity and Stability

PT Provider employees and any suppliers they may utilize are aware of the significance of the homogeneity and stability of test specimens for the results of the Proficiency Testing Program. Proficiency testing items are provided in cooperation with BETOTECH, s.r.o., Beroun 660, Beroun. The homogeneity and stability of specimens is ensured in the following ways:

1. the material used for the production of samples is always taken from the same production and is of the same production date; and/or
2. by dividing the specimens produced in different batches in order to ensure specimen homogeneity during testing of physical-mechanical and durability properties,
3. using a single type of mold-release preparation,
4. using a single type of molds from the same material for one type of test,
5. storing all specimens together under identical conditions,
6. checking all specimens before dispatching to participants.
7. Store the test specimens for strength tests in accordance with Article 5.5.2 of EN 12390-2 [11]. The PT organiser prefers to store in water. Otherwise, follow the requirements of the relevant standards.
8. The four sides of the test specimens according to EN 12390-8 [3] are adapted according to Article 6.1 of this standard.
9. The test specimens for frost resistance test according to ČSN 731322 [5] are subjected to homogeneity test by resonance method according to ČSN 731372 [12].

2.3 Instructions for Eliminating Major Sources of Errors and Risks

Participants of the PTP are required to:

- Ensure that samples are stored and transported in accordance with EN 12390-2 [11],
- Handle proficiency testing items in the same manner as most routinely tested samples,
- Follow the instructions of the PT provider responsible for the implementation of the PTP, particularly regarding the type of test performed, the number of determinations of results, and the timing of the testing,
- Report measurement uncertainty in accordance with their documented procedures, including the appropriate coverage factor. Unless otherwise specified, participants shall use a coverage factor of 2, corresponding to a confidence level of approximately 95
- Adhere to the rules and principles of ethical behavior, avoiding unfair practices that could negatively impact the evaluation of the PT program,

- Follow occupational health and safety and fire protection regulations, using only electrical equipment and instruments with valid inspections,
- Submit the results of the proficiency testing items, including measurement uncertainties, to the PT provider by the deadline specified in section 1.

3 Procedures used in the Statistical Analysis of Laboratory Results

Procedures used in the statistical analysis of proficiency testing programs can be found at ptprovider.cz.

4 Certificate of Participation and the Final Report on the Results of Interlaboratory Comparison

The PT Provider gives expert commentary on participant efficiency evaluation in the Final Report as part of training courses the PT Provider organises. The Final Report preserves the anonymity of the PTP participants. Each participant, or the participant's test results, is represented by an ID number. The Certificate of Participation in the PT programme is part of the Final Report. The Certificate is unique to each participant and includes the participant's ID number.

5 Safeguards for Confidentiality

The identity of PTP participants is confidential and only known to persons/subjects involved with the PTP. All participant information is considered confidential by the PT Provider. The participant may renounce this confidentiality for the purposes of discussion and mutual assistance until the PTP results are obtained. The PT Provider reveals the proficiency testing results to no third party with the sole exception of a written request by a regulatory authority submitted prior to the commencement of the PTP and which has been granted a written consent by the PTP participants.

6 Related Documents

- Quality Handbook of the PT Provider at the SZK FAST
- Cancellation and Complaint Proceedings available at <http://ptprovider.cz/?lang=en> [9]
- MPA 20 – 01 - . . . for application of EN ISO/IEC 17043 Concordance Assessment – General Requirements for Proficiency Testing in the Accreditation System of the Czech Republic.

References

- [1] EN 12390-3. *Testing hardened concrete - Part 3: Compressive strength of test specimens*. 2020.
- [2] EN 12390-7. *Testing hardened concrete - Part 7: Density of hardened concrete*. 2020.
- [3] EN 12390-8. *Testing hardened concrete - Part 8: Depth of penetration of water under pressure*. 2020.

- [4] EN 480-11. *Admixtures for concrete, mortar and grout - Test methods - Part 11: Determination of air void characteristics in hardened concrete*. 2006.
- [5] ČSN 73 1322. *Determination of frost resistance of concrete*. 2003.
- [6] ČSN 73 1324. *Determination of grindability of concrete*. 2003.
- [7] ČSN 73 1326. *Resistance of cement concrete surface to water and defrosting chemicals*. 2003.
- [8] CEN/TS 12390-9. *Testing hardened concrete - Part 9: Freeze-thaw resistance - Scaling*. 2007.
- [9] *Cancellation and Complaint Proceedings* – available at www.ptprovider.cz.
- [10] EN 206:2013+A2:2021. *Concrete - Specification, performance, production and conformity*. 2021.
- [11] EN 12390-2. *Testing hardened concrete - Part 2: Making and curing specimens for strength tests*. 2020.
- [12] ČSN 731372. *Non-destructive testing of concrete - Testing of concrete by resonance method*. 2012.